

CORCHEM® 239 FIRE TUBE COATING

| | |
|----------------------------|---|
| GENERAL | Proprietary technology including densely cross-linked reactive polymer catalyzed to form a barrier structure that is extremely chemically inert with a high heat deflection temperature while maintaining critical heat transfer properties for efficient function of fire tubes. |
| DESCRIPTION | Heavy-duty coating designed to cure at ambient temperature conditions providing exceptional elevated temperature protection for surfaces in severe chemical and physical environments. It is formulated to be extremely adhesive, hard, tough and abrasion resistant. |
| USE | Intended for fire tube's in oil field treaters handling hot crude, brine and waste water at oil field production sites including water solutions containing carbon dioxide, hydrogen sulfide and methane gases, salts, detergents, many acids, alkali, and other chemicals. Also suggested as a protective coating for hot transfer lines and steam generating equipment; steel boiler stacks and shells; furnaces, exhaust manifolds and mufflers. The principal use is in chemical problem areas such as oil field production and chemical manufacturing and processing facilities. |
| SERVICE LIMITATIONS | Temperature resistance up to 450°F depending upon the individual exposure. CONTACT CORCHEM® FOR SPECIFIC RECOMMENDATIONS BEFORE PROCEEDING for immersion service and exposure to corrosive chemicals, elevated temperatures and/or pressures, or use with cathodic protection systems. Avoid sudden depressurization of lining. |
| COLORS | Black. |
| FINISH | Medium Gloss. |
| NOTE: | Color and gloss variation may occur due to different induction and heat/dry time cure cycles used or if subject to moisture before curing is complete. Color and gloss retention are affected by exposure to elevated temperatures. Chalking will occur with extended exposure to sunlight (UV). |
| PACKAGING | 1-gallon pre-measured packaged kits. |
| COMPONENTS | Two. By volume 1 to 3 (Component A : Component B). |
| HAZMAT DATA | Hazard Class 3 – Flammable, Sub-Class 8 – Corrosive. This material ships in any quantity via common carrier only. <i>Refer to individual Component's Safety Data Sheet for complete Hazmat and Safety information.</i> |
| SHELF LIFE | 1 year from shipment date protected between 40°F and 100°F in its original sealed container. |
| VOLUME SOLIDS | 42% |
| VOC CONTENT | 475 gms/l or 3.95 lbs/gal. Conforms to United States National Volatile Organic Compound Emission Standards. |
| SURFACE PREPARATION | Round off sharp edges and rough welds. Burrs and weld spatter should be completely removed. Surfaces must be clean, dry and free of any visible dirt, chalk, grease, oils, salts, and deleterious materials before application is performed. Vacuum the topside of all horizontal and sloped surfaces. |
| CARBON STEEL | Immersion or Severe Exposures: NACE No. 1 / SSPC-SP-5 (White Metal Blast Cleaning). Metal surfaces should have an anchor profile of 1.0 to 1.5 mils. |
| WELDING | Welding should precede coating. If already coated, follow instructions in American Welding Society, ANSI Standard Z49.1 Safety in Welding and Cutting. |

DRY COVERAGE Theoretical (no loss): 672 sq. ft. per gallon for one mil (.001). When computing coverage allow for application loss and surface irregularities.

DRY FILM THICKNESS 2.0 to 3.0 mils per coat. Two or more coats to achieve a total system dry film thickness of 4.0 to 6.0 mils. Multiple applications are recommended and may be necessary to achieve the specified or desired film thickness or due to variations in design configurations, application equipment, temperature and other factors.

CAUTION **DO NOT EXCEED 2.0 TO 3.0 MILS PER COAT OR RECOMMENDED TOTAL SYSTEM DRY FILM THICKNESS.** This material is designed for high heat transfer, exceeding the recommended dry film thickness may cause heat retention adversely effecting performance and damaging the coating.

POT LIFE >4 hours @ 70°F (mixed one-gallon kit). Pot life is significantly shorter for higher temperatures or larger quantities and longer for lower temperatures or smaller quantities.

THINNER **Use of Thinner is NOT recommended.**
If thinner is used, use only CORCHEM® 4 Thinner. Thin only if required for proper application. Do not exceed applicable volatile organic compound (VOC) regulations. Thinner added:

| | |
|-----------------------------------|-----------------------------------|
| 05% - 490 gms/lit or 4.08 lbs/gal | 10% - 504 gms/lit or 4.20 lbs/gal |
| 15% - 516 gms/lit or 4.30 lbs/gal | 20% - 527 gms/lit or 4.39 lbs/gal |

TEMPERATURES Apply at 35°F to 125°F (Air and Surfaces) and 5°F above the dew point. Sudden and/or substantial temperature change during curing process or in-service conditions can cause film defects.

MATERIAL MIXING All equipment should be cleaned and flushed with CORCHEM® 4 THINNER. Pre-mix each component separately prior to combining as follows: **Add 1-Part Component A into 3-Parts Component B.** Do not vary proportions. Power-stir, until completely mixed and continue agitation during application. Strain only if required for proper application. Do not allow catalyzed material to stand in equipment after use! Clean immediately with CORCHEM® 4 THINNER or Methyl Ethyl Ketone (MEK).

APPLICATION METHODS Conventional air spray (pressure pot) or airless spray (hot pot) and brush (small areas). See applicable Section below for more information. Plural Component Spray is NOT suitable for application of this material.

PLURAL COMPONENT Not suitable

AIRLESS Graco or equal. Airless pump ratio 30:1 or higher including outlet filter with 60 mesh screen, 3/8" ID or larger high pressure solvent resistant fluid line, Silver plus or equivalent gun with .013" to .017" RAC spray tip, 1/2" I.D. or larger air supply line. Continuous air source capable of 80 – 100 CFM @ 80 to 100 psi inbound pressure at pump.

CONVENTIONAL Binks or equal. Pressure material pot with mechanical agitator, dual air regulators, air-gages, and oil and moisture separators. Binks 2100 spray gun (external mix), 66SS fluid nozzle, 563 fluid needle, 6650 or 665K air cap, -or- DeVilbiss JGA or MBC with E setup and 704 air cap, 1/2" I.D. or larger high solvent resistant fluid line and 1/2" I.D. or larger air-supply line. Continuous air source capable of 20 cfm or more at 60 psi per nozzle and 60 psi to the pot.

NOTE Regulate pressure as required for proper application. Proportionally adjust pressure higher for smaller hose diameter and/or longer hose length and adjust pressure lower for larger hose diameter and/or shorter hose length. Select tip angles and orifice diameters according to application needs.

BRUSH Short hair or natural bristle.

APPLY In a thin wet coat, allow the material to flash off several minutes but not dry completely, then apply multiple passes to produce an even wet coat to achieve a dry film thickness of 2.0 to 3.0 mils. Ensure seams and irregularities are completely covered. Application below minimum or above maximum suggested dry film thickness ranges might adversely affect performance, (see "CAUTION" above).

CURING TIME This curing schedule is predicated upon application conditions where the mixed product, substrate, and ambient air temperatures are the same:

| Temperature | 50°F | 70°F | 90°F |
|------------------------|----------|----------|----------|
| Minimum Recoat Time | 8 Hours | 4 Hours | 2 Hours |
| Maximum Recoat Time | 48 Hours | 24 Hours | 12 Hours |
| Immersion – Final Cure | 96 Hours | 48 Hours | 24 Hours |

Curing times are significantly shorter for higher temperatures or lower thickness and are longer for lower temperatures or higher thickness. Curing times are affected by the method of application; thickness of applied film; the quantity of thinner (if used); the amount of ventilation and air circulation; relative humidity; etc. (refer to RECOAT AND REPAIR Section if coating reaches complete cure and hardness or if subjected to extended exposure to sunlight).

NOTE Heat curing may be used to increase drying speed and resistance properties. After the final coat has been applied, allow the minimum flash off/curing time necessary to prevent blistering and defects, then gradually raise the temperature not more the 50°F every 30 minutes until the substrate reaches 250°F to 300°F and bake for 1.5 hours. Contact CORCHEM® for complete instructions and heat cure times.

RECOAT AND REPAIR If material has reached complete cure and hardness, or if subjected to extended exposure to sunlight, uniformly abrade the surface and feather the edges. The surface must be roughened sufficiently to provide a profile adequate to ensure a mechanical bond.

INSPECTION Check for desired dry film thickness, (relevant standards: ASTM D7019 / SSPC PA 2), and for pinholes, holidays, bare areas, (relevant standards: ASTM D5162 "Method A" / NACE SP0188 "Low-Voltage Wet Sponge Test"), etc. before placing into operating service.

PPE / CLOTHING Refer to the Safety Data Sheet (SDS) for complete safety information. Wear protective garments, shoes, goggles, and filter masks. Use protective barrier creams on exposed skin areas.

TANKS & VESSELS Refer to the Safety Data Sheet (SDS) for complete safety information. Use explosion-proof lighting and electrical equipment, non-sparking tools, clothes and shoes. Ground all structures and equipment. Use procedures that prevent static electrical sparks. Wear properly fitted appropriate NIOSH/MSHA approved fresh air respirator such as MSA or equal with 1/4" I.D. or larger air supply line connected directly to proper air source during and after application unless air monitoring demonstrates vapor/mist levels are within safe limits. Use suction type exhaust fans and blowers with sufficient cfm capacity to keep solvent vapors below 20% of the explosive limit. **CAUTION!** Air circulation and exhausting of solvent vapors must be continued until the coatings have fully cured to insure that no potential for fire, explosion or health hazard remains.

SAFETY INFORMATION

THIS PRODUCT CONTAINS ALCOHOLS, KETONES, AND PETROLEUM DISTILLATES. DO NOT USE IF YOU HAVE HAD A REACTION TO THESE MATERIALS.

WARNING! FLAMMABLE! VAPOR HARMFUL! CAUSES SEVERE EYE AND SKIN BURNS. MAY CAUSE SKIN SENSITIZATION OR OTHER ALLERGIC RESPONSES. HARMFUL OR FATAL IF SWALLOWED!

Keep away from heat, sparks, and open flame. Use only with adequate ventilation. Prevent breathing of vapor or spray mists. Wear a properly fitted appropriate respirator during application and until all vapors and spray mists are gone. Prevent contact with eyes and skin. Do not take internally. Keep closures tight and upright to prevent leakage. Keep container closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations. **FIRST AID:** In case of skin contact, wash thoroughly with soap and water; for eyes, flush immediately with plenty of water for 15 minutes and call a physician. Remove and wash contaminated clothing before reuse. (Discard contaminated shoes). If inhaled, remove to fresh air. If breathing difficulty persists or occurs later, consult a physician and have label and SDS information available. If swallowed, **CALL A PHYSICIAN IMMEDIATELY. DO NOT INDUCE VOMITING.**

IN CONFINED SPACES AND TANKS OBEY SPECIAL SAFETY AND EQUIPMENT INSTRUCTIONS!

FOR INDUSTRIAL USE BY PROFESSIONAL APPLICATORS ONLY. NOT INTENDED FOR SALE TO THE GENERAL PUBLIC. This product is not to be sold or delivered to any person under 18 years of age. **KEEP OUT OF THE REACH OF CHILDREN! IF, FOR ANY REASON, ADDITIONAL PRODUCT AND SAFETY INFORMATION, INSTRUCTIONS OR EXPLANATIONS ARE NEEDED, CONTACT CORCHEM® IMMEDIATELY!**

LIMITED WARRANTY

WARRANTY & LIMITATION OF SELLER'S LIABILITY: CORCHEM CORPORATION warrants only that its coatings represented herein meet the formulation standards of CORCHEM® CORPORATION.

THE ABOVE WARRANTY SHALL BE IN LIEU OF ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTIONS ON THE FACE HEREOF.

The buyer's sole and exclusive remedy against CORCHEM® CORPORATION shall be for replacement of the product, in the event a defective condition of the product should be found to exist. NO OTHER REMEDY (INCLUDING, BUT NOT LIMITED TO, INCIDENTAL OR CONSEQUENTIAL DAMAGES FOR LOST PROFITS, LOST SALES, INJURY TO PERSON OR PROPERTY, OR ANY OTHER INCIDENTAL OR CONSEQUENTIAL LOSS) SHALL BE AVAILABLE TO THE BUYER. The sole purpose of this exclusive remedy shall be to provide buyer with replacement of the product if any defect in materials is found to exist. This exclusive remedy shall not be deemed to have failed its essential purpose so long as CORCHEM® CORPORATION is willing and able to replace the defective materials.

Technical and application information is provided for the purpose of establishing a general profile of the coating and proper coating application procedures. Test performance results were obtained in a controlled environment and CORCHEM® CORPORATION makes no claim these tests or any other tests, accurately represent all environments. As application, environmental and design factors can vary significantly, due care should be exercised in the selection and use of the coating.

PUBLISHED TECHNICAL DATA AND INSTRUCTIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE.
CONTACT YOUR CORCHEM® REPRESENTATIVE FOR CURRENT TECHNICAL DATA AND INSTRUCTIONS.

CORCHEM® 239 FIRE TUBE COATING
COPYRIGHT© 2016 by CORCHEM®.
Document ID: C239-2-TB-09062016-0728
Revision: 2

